



Dimension: (UNIT:mm)

A	160.0 ± 7.5
B	80.0 ± 0.6
C	40.0 ± 1.0
D	60.0 ± 1.0
E	116Min
F	40.0 ± 1.5
G	
H	



Test conditions

AL: F=1.0KHz U=0.3V N=10Ts

Effective parameter

	C1(mm) ⁻¹	Ae(mm ²)	Le(mm)	Ve(mm ³)	Weight(g)
	0.235	1600	376	659200	≈ 1580

Properties of core sets under power conditions

Core halves for general purpose transformers and power applications.

Clamping force for Al measurements, 5+/-2N

Grade	AL (nH)	μe	AIR GAP μm	Type number
P3	10800±25%		≈0	EE160-P3

Grade	B (mT)at	Core loss (w) at		
	H=250 A/m F=25KHz T=100°C	f=100 KHz B=100mT T=100°C	f=100 KHz B=200mT T=100°C	F=400 KHz B=50mT T=100°C
P3	≥ 340			

Properties of core sets under power conditions (continued)

Grade	B (mT)at	Core loss (w) at			
	H=250 A/m F=25KHz T=100°C	F=500 KHz B=50mT T=100°C	F=500 KHz B=100mT T=100°C	F=1.0MHz B=30mT T=100°C	F=3.0MHz B=10mT T=100°C
P3	≥ 340				

Note:

- 1: Document is the property of FUAN Inc & is not allow to be duplicated without authorization
- 2: RoHS compliant.