




Ferrite core




i e io			
o o ti i e io			
			t et
28.0#0.40	16.0#0.40	13.0#0.40	24.50
29.1a Ul	15.0a Jb	14.0a Ul	



Test Conditions

AL: F=10.0KHz U=0.3V N=10Ts



Effective parameter

	Ve(mm ³)	Ae(mm ²)	Le(mm)
	4990	76.0	65.6

Coating

The core are coated with epoxy, flame retardant in accordance with "UL 94V-0" file number E228348.


The colour is green.

Ring core data


GRADE	AL(nH)	μi	TYPE NUMBER
P3	3500±25%	≈2300	T28/16/13/P3
H5K	7300±25%	≈5000	T28/16/13/H5K
H7K	10200±25%	≈7000	T28/16/13/H7K
H10K	14500±30%	≈10000	T28/16/13/H10K

Note:


- 1: Document is the property of FUAN Inc & is not allowed to be duplicated without authorization
- 2: RoHS compliant.




P3



H5K



H7K



H10K